

ABSTRACT

The present invention is provided to manufacture a semiconductor device capable of preventing loss of dopants due to external diffusion thereof from a junction area by forming a cobalt mono-silicide film through a first
5 RTP process, implanting ions not serving as a donor or an acceptor with a low energy and a low dose to make the film amorphous, and then forming a cobalt silicide film through a second RTP process.